## QC ABSTRACT

**NAME OF WORK:** Construction of RCC Drain at 10th A Main A Sector in Ward No 04

| SL NO | Item Of Work | Name of Test | Frequency of Test/Quantity | Executed Quantity | Number of Tests Required | Number of Tests Conducted |
|---|---|---|---|---|---|---|
| | | Materials | | | | |
| 1 | Cement | Fineness by dry sieving | One Test | | 1 | 1 |
| | | Finess by Air permeablity method | One Test | | 1 | 1 |
| | | Density | One Test | | 1 | 1 |
| | | Standard Consistency | One Test | | 1 | 1 |
| | | Initial Setting time | One Test | | 1 | 1 |
| | | Final Setting time | One Test | | 1 | 1 |
| | | Soundness (Le Chatelier's Method) | One Test | | 1 | 1 |
| | | Compressive Strength | One Test | | 1 | 1 |
| 2 | Coarse aggregate(40 mm down size) | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Flakiness Index | One Test | | 1 | 1 |
| | | Elongation Index | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Bulk Density(Loose) | One Test | | 1 | 1 |
| | | Bulk Density(Compacted) | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| 3 | Coarse aggregate(20 mm down size) | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Flakiness Index | One Test | | 1 | 1 |
| | | Elongation Index | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Bulk Density(Loose) | One Test | | 1 | 1 |
| | | Bulk Density(Compacted) | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| | | Aggregate crushing Value | One Test | | 1 | 1 |
| | | Aggregate Impact Value | One Test | | 1 | 1 |
| 4 | Fine aggregate | SIEVE ANALYSIS | One Test | | 1 | 1 |
| | | Water Absorption | One Test | | 1 | 1 |
| | | Specific Gravity | One Test | | 1 | 1 |
| | | Material finer than 75 micron | One Test | | 1 | 1 |
| 5 | Steel | Bend test | One Test | | 1 | 1 |
| | | Tensile Test | One Test | | 1 | 1 |
| | | Yield Test | One Test | | 1 | 1 |
| | | ReBend test | One Test | | 1 | 1 |
| 6 | Precast (100mm) | Core Compressive Strength | One Test | | 1 | 1 |
| | | Corrected Cylinder Compressive Strength | One Test | | 1 | 1 |
| | | Equivalent Cube Compressive Strength | One Test | | 1 | 1 |
| 7 | Precast (200mm) | Core Compressive Strength | One Test | | 1 | 1 |
| | | Corrected Cylinder Compressive Strength | One Test | | 1 | 1 |
| | | Equivalent Cube Compressive Strength | One Test | | 1 | 1 |
| 8 | RCC(M20) | Compressive Strength(7days and 28days) | 4 set /31-50 cum | 41.76 | 8 | 8 |

ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರ
ಬೆಂಗಳೂರು ಉಪನಗರ ಉಪವಿಭಾಗ.
ಬೆಂಗಳೂರು-106

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | CP-2020-11-23-49 **Date: 15-07-19** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| **Agency** | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 12-07-19 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification ,<br>IS 4031 (Part 1,2 3,4,5, 6,11):1988<br>IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4<br>IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5<br>IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6<br>IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5<br>IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6 |
| **Date of test** | : | 13-07-19 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

| SLNo. | Physical properties | Results | Requirement as per IS 12269: 2013 |
|---|---|---|---|
| 1 | Fineness by dry sieving (%) | 2.2 | - |
| 2 | Finess by Air permeablity method ($m^2$/kg,Min) | 249.5 | 225$m^2$/kg, Min |
| 3 | Density (gm/cc) | 3.11 | - |
| 4 | Standard Consistency (%) | 27.5% | Not specified |
| 5 | Initial Setting time | 170 minutes | Not less than 30 minutes |
| 6 | Final Setting time | 260 minutes | Not more than 600 minutes |
| 7 | Soundness (Le Chatelier's Method) | 1.5mm | Not more than 10 mm |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**



****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

## TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2020-11-23-49** **Date: 10-08-19** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| **Agency** | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 12-07-19 |
| **Sample Type** | : | Birla Super 53grade |
| **Reference to BIS codes** | : | IS 12269 2013, 53 Grade Ordinary Portland cement Specification ,<br>IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5<br>IS 4031 Part 6, Determination of Compressive Strength, Clause 6 |
| **Date of test** | : | 13-07-19 |
| **Environmental Conditions during test** | : | Temperature: 26°C<br>Humidity: 72% |

**Compressive Strength**

| Sl.No. | Physical properties | Results | Requirement as per IS 12269: 2013 |
|---|---|---|---|
| 1 | 3 Days | 28.5N/mm$^2$ | Not less than 27 N/mm$^2$ |
| 2 | 7 Days | 39.0N/mm$^2$ | Not less than 37 N/mm$^2$ |
| 3 | 28 Days | 58.5N/mm$^2$ | Not less than 53 N/mm$^2$ |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager



****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

# TEST REPORT OF FINE AGGREGATE

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2020-11-23-49** **Date: 15-07-19** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| **Agency** | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 12-07-19 |
| **Sample Type** | : | Fine Aggregate |
| **Reference to BIS codes** | : | IS 383 : 2016 (Specification for Coarse and fine Aggregates)<br>IS: 2386 :1963(Part - 1, 3) RA2012<br>IS 2386 Part 1: Particle Size and Shape<br>IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption |
| **Date of test** | : | 12-07-19 |
| **Total weight taken** | : | 1000 grams |

| Sl.no | Sieve Size | Weight Retained (gms) | Cumulative Weight Retained (gms) | % Cumulative Weight Retained | % Passing | Requirement as per IS 383:2016 | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | | | | | Grading Zone I | Grading Zone II | Grading Zone III | Grading Zone IV |
| 1 | 10 mm | 0 | 0 | 0.0 | 100.0 | 100 | 100 | 100 | 100 |
| 2 | 4.75 mm | 27 | 27 | 2.7 | 97.3 | 90-100 | 90-100 | 90-100 | 95-100 |
| 3 | 2.36 mm | 55 | 82 | 8.2 | 91.8 | 60-95 | 75-100 | 85-100 | 95-100 |
| 4 | 1.18 mm | 239 | 321 | 32.1 | 67.9 | 30-70 | 55-90 | 75-100 | 90-100 |
| 5 | 600 micron | 205 | 526 | 52.6 | 47.4 | 15-34 | 35-59 | 60-79 | 80-100 |
| 6 | 300 micron | 203 | 729 | 72.9 | 27.1 | 5-20 | 8-30 | 12-40 | 15-50 |
| 7 | 150 micron | 191 | 920 | 92.0 | 8.0 | 0-10 | 0-10 | 0-10 | 0-15 |
| 8 | Pan | 80 | 1000 | 100.0 | 0.0 | --- | --- | --- | --- |

**Result :The tested Sample Conforms to Grading Zone II**



CIVIL Pro Sig Date BANGALORE

M : 9972924526 Tel: +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL|
GEO TECHNICAL| PROJECT MANAGEMENT| SURVEYING SERVICES |

# TEST REPORT OF FINE AGGREGATE

**Lab ID** : **CP-2020-11-23-49** **Date: 15-07-19**

## PHYSICAL PROPERTIES

| Sl.no | Tests | Result | Requirements as per IS 383:2016 |
|---|---|---|---|
| 1 | Water Absorption(%) | 1.5 | – |
| 2 | Specific Gravity | 2.59 | – |
| 3 | Material finer than 75 micron(%) | 6.9 | Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10% |

• The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

**FOR CIVIL Pro.**

**R KARTHIK RECHAN**
Authorized Signatory
**Quality Manager**

CIVIL Pro BANGALORE Sig. Date



****End of Report****

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರ
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ,
ಬೆಂಗಳೂರು-106

Format No: CP/TF/01

# TEST RESULTS OF STEEL

Date: 31-07-19

| | | |
|---|---|---|
| Lab ID | : | CP-2020-11-23-49 |
| Customer | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Address | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Project Name | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| Agency | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| Customer's Reference | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| Source of Sample | : | Sample supplied by Agency |
| Sample Condition | : | Satisfactory |
| Date of Receipt | : | 30-07-19 |
| Sample Type | : | Sunvik |
| Reference to BIS codes | : | IS 1786-2008, IS:1608-2005(RA 2011), IS 1599-2012. |
| Date of test: | : | 30-07-19 |

| Sl.No | Identification of sample | Grade of the sample | Diameter of the steel bar | Weight of the sample | Yield stress | Tensile strength | Elongation | Bend test | Rebend test |
|---|---|---|---|---|---|---|---|---|---|
| | | | (mm) | (kg/m) | (N/mm2) | (N/mm2) | (%) | | |
| 1 | Sunvik | Fe500 | 8 | 0.391 | 512 | 652 | 20.0% | Satisfactory | Satisfactory |
| 2 | Sunvik | Fe500 | 10 | 0.616 | 528 | 672 | 20.0% | Satisfactory | Satisfactory |
| 3 | Sunvik | Fe500 | 12 | 0.888 | 544 | 668 | 20.0% | Satisfactory | Satisfactory |

• The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig Date BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
*End of Report*

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

Date: 10/08/2019

| | | |
|---|---|---|
| Lab ID | : | CP-2020-11-23-49 |
| Customer | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Address | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Project Name | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| Agency | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| Customer's Reference | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| Source of Sample | : | Sample supplied by Agency |
| Sample Condition | : | Satisfactory |
| Date of Receipt | : | 05-08-19 |
| Customer ID | : | Drain Bottom Slab |
| Sample Type /Size | : | 150X150X150 mm |
| Sample grade/Age | : | M20 / 7 Days Compressive Strength |
| Reference to BIS codes | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| Date of test | : | 10/08/2019 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Slab | M20 | 03/08/2019 | 10/08/2019 | 149.44 X 149.25 X 151.15 | 22304 | 8.725 | 405.0 | 18.2 | 18.1 |
| 2 | Drain Bottom Slab | M20 | 03/08/2019 | 10/08/2019 | 150.80 X 149.01 X 151.92 | 22470 | 8.409 | 405.7 | 18.1 | |
| 3 | Drain Bottom Slab | M20 | 03/08/2019 | 10/08/2019 | 150.08 X 151.50 X 151.74 | 22736 | 8.174 | 410.2 | 18.0 | |

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರ
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-106

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

| | | |
|---|---|---|
| **Lab ID** | : | CP-2020-11-23-49 **Date: 14/08/2019** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| **Agency** | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 09-08-19 |
| **Customer ID** | : | Drain Side Wall |
| **Sample Type /Size** | : | 150X150X150 mm |
| **Sample grade/Age** | : | M20 / 7 Days Compressive Strength |
| **Reference to BIS codes** | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| **Date of test** | : | 14/08/2019 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall | M20 | 07/08/2019 | 14/08/2019 | 149.82 X 151.59 X 150.84 | 22711 | 8.725 | 415.6 | 18.3 | 18.5 |
| 2 | Drain Side Wall | M20 | 07/08/2019 | 14/08/2019 | 151.88 X 149.00 X 150.26 | 22630 | 8.409 | 428.5 | 18.9 | |
| 3 | Drain Side Wall | M20 | 07/08/2019 | 14/08/2019 | 150.25 X 151.24 X 151.14 | 22724 | 8.174 | 412.0 | 18.1 | |

* The results obtained are satisfactory as per standard requirements.

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರ
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ
ಬಿ.ಬಿ.ಎಂ.ಪಿ, ಬೆಂಗಳೂರು-106


****End of Report****

M : 9972924826 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

| | | |
|---|---|---|
| **Lab ID** | : | **CP-2020-11-23-49** **Date: 04/09/2019** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| **Agency** | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 09-08-19 |
| **Customer ID** | : | Drain Side Wall |
| **Sample Type /Size** | : | 150X150X150 mm |
| **Sample grade/Age** | : | M20 / 28 Days Compressive Strength |
| **Reference to BIS codes** | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| **Date of test** | : | 04/09/2019 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall | M20 | 07/08/2019 | 04/09/2019 | 151.16 X 151.45 X 150.16 | 22893 | 8.927 | 538.6 | 23.5 | 23.3 |
| 2 | Drain Side Wall | M20 | 07/08/2019 | 04/09/2019 | 150.37 X 149.30 X 151.83 | 22450 | 9.047 | 505.0 | 22.5 | |
| 3 | Drain Side Wall | M20 | 07/08/2019 | 04/09/2019 | 151.03 X 149.85 X 151.35 | 22632 | 8.536 | 538.0 | 23.8 | |

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro. Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರ
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ,
ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು-106


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

| | | |
|---|---|---|
| Lab ID | : | CP-2020-11-23-49 Date: 20/08/2019 |
| Customer | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Address | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Project Name | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| Agency | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| Customer's Reference | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| Source of Sample | : | Sample supplied by Agency |
| Sample Condition | : | Satisfactory |
| Date of Receipt | : | 16-08-19 |
| Customer ID | : | Drain Bottom Slab |
| Sample Type /Size | : | 150X150X150 mm |
| Sample grade/Age | : | M20 / 7 Days Compressive Strength |
| Reference to BIS codes | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| Date of test | : | 20/08/2019 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Slab | M20 | 13/08/2019 | 20/08/2019 | 151.25 X 151.82 X 151.13 | 22963 | 8.725 | 413.8 | 18.0 | 18.3 |
| 2 | Drain Bottom Slab | M20 | 13/08/2019 | 20/08/2019 | 149.79 X 150.47 X 151.23 | 22539 | 8.409 | 416.7 | 18.5 | |
| 3 | Drain Bottom Slab | M20 | 13/08/2019 | 20/08/2019 | 149.30 X 150.52 X 150.61 | 22473 | 8.174 | 413.3 | 18.4 | |

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

| | | |
|---|---|---|
| **Lab ID** | : | CP-2020-11-23-49 **Date: 10/09/2019** |
| **Customer** | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Address** | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| **Project Name** | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| **Agency** | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| **Customer's Reference** | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| **Source of Sample** | : | Sample supplied by Agency |
| **Sample Condition** | : | Satisfactory |
| **Date of Receipt** | : | 16-08-19 |
| **Customer ID** | : | Drain Bottom Slab |
| **Sample Type /Size** | : | 150X150X150 mm |
| **Sample grade/Age** | : | M20 / 28 Days Compressive Strength |
| **Reference to BIS codes** | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| **Date of test** | : | 10/09/2019 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Bottom Slab | M20 | 13/08/2019 | 10/09/2019 | 149.86 X 150.33 X 149.07 | 22530 | 8.927 | 528.8 | 23.5 | 22.9 |
| 2 | Drain Bottom Slab | M20 | 13/08/2019 | 10/09/2019 | 151.78 X 149.96 X 149.88 | 22760 | 9.047 | 504.6 | 22.2 | |
| 3 | Drain Bottom Slab | M20 | 13/08/2019 | 10/09/2019 | 151.70 X 149.53 X 150.97 | 22684 | 8.536 | 522.4 | 23.0 | |

* The results obtained are satisfactory as per standard requirements

**Note:**

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರ
ಯಲಹಂಕ ಉಪನಗರ ಉಪವಿಭಾಗ,
ಬೆ.ಮ.ನ.ಪ. ಬೆಂಗಳೂರು-106


****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

# TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/09/2019

| | | |
|---|---|---|
| Lab ID | : | CP-2020-11-23-49 |
| Customer | : | Assistant Executive Engineer, Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Address | : | Yelahanka Satellite Town Sub Division, BBMP, Bangalore. |
| Project Name | : | Construction of RCC Drain at 10th A Main A Sector in Ward No 04 |
| Agency | : | Sri.Vijayakumar R, No:48/5, C Block, Sahakaranagar, Bangalore |
| Customer's Reference | : | EE(YNK.D)E-PMT-09/W.O/38/2019-20 |
| Source of Sample | : | Sample supplied by Agency |
| Sample Condition | : | Satisfactory |
| Date of Receipt | : | 21-08-19 |
| Customer ID | : | Drain Side Wall |
| Sample Type /Size | : | 150X150X150 mm |
| Sample grade/Age | : | M20 / 28 Days Compressive Strength |
| Reference to BIS codes | : | IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5 |
| Date of test | : | 16/09/2019 |

| Sl. No. | Identification Mark | Grade of concrete | Date of Casting | Date of Testing | Dimension of the Specimen (mm) | Cross sectional area (Sq.mm) | Weight of the sample (kg) | Failure Load (KN) | Compressive strength ($N/mm^2$) | Average Compressive Strength ($N/mm^2$) |
|---|---|---|---|---|---|---|---|---|---|---|
| 1 | Drain Side Wall | M20 | 19/08/2019 | 16/09/2019 | 150.31 X 151.41 X 149.63 | 22759 | 8.927 | 530.8 | 23.3 | 22.9 |
| 2 | Drain Side Wall | M20 | 19/08/2019 | 16/09/2019 | 151.06 X 151.02 X 151.35 | 22814 | 9.047 | 507.4 | 22.2 | |
| 3 | Drain Side Wall | M20 | 19/08/2019 | 16/09/2019 | 149.93 X 149.12 X 150.55 | 22358 | 8.536 | 517.8 | 23.2 | |

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig. Date BANGALORE

Page 1/1
****End of Report****